

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> : <b>B05D 7/24</b>	<b>A1</b>	(11) International Publication Number: <b>WO 99/32235</b> (43) International Publication Date: 1 July 1999 (01.07.99)
<p>(21) International Application Number: PCT/GB98/03838</p> <p>(22) International Filing Date: 18 December 1998 (18.12.98)</p> <p>(30) Priority Data: 9726807.2 18 December 1997 (18.12.97) GB</p> <p>(71) Applicant (for all designated States except US): BTG INTERNATIONAL LIMITED (GB/GB); 10 Fleet Place, Limeburner Lane, London EC4M 7SB (GB).</p> <p>(72) Inventors; and (75) Inventors/Applicants (for US only): BADIYAL, Jas, Pal, Singh [GB/GB]; Redgate House, Wolsingham, Co. Durham DL13 3HH (GB). HUTTON, Simon, James [GB/GB]; University of Durham, Chemistry Dept., Science Laboratories, South Road, Durham DH1 3LE (GB).</p> <p>(74) Agent: NEVILLE, Peter, Warwick; BTG International Limited, Patents Division, 10 Fleet Place, Limeburner Lane, London EC4M 7SB (GB).</p>		<p>(81) Designated States: AU, CA, JP, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p><b>Published</b> <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>
<p>(54) Title: APPLYING FLUOROPOLYMER FILM TO A BODY</p> <p>(57) Abstract</p> <p>A thin fluoropolymer film is bonded to a substrate for medical, filtration or packaging purposes by using a pulsed or combination of gas and electrical pulsed cold plasma polymerisation procedures.</p> <div data-bbox="1045 1814 1403 1950" style="text-align: right;"><i>Express Mail Label No. EV 507 272 276 US</i></div>		

*FOR THE PURPOSES OF INFORMATION ONLY*

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

## APPLYING FLUOROPOLYMER FILM TO A BODY

This invention relates to a method of applying a fluoropolymer film to a body and to bodies so treated.

5

Oleophobic or superhydrophobic surfaces are desired for a number of applications. The invention arises out of investigations of the phenomenon of surfaces with lower energy than ptfe (polytetrafluoroethylene) by taking advantage of the effect arising from attachment of  $\text{CF}_3$  groups to a variety of materials.

10

The invention may be applicable to thin films usable in polymeric filter media and to cold plasma treatments to create low energy surfaces upon low-cost thermoplastics and natural media, and to the functionalisation of fluorinated polymers such as PTFE and PVDF (polyvinylidene difluoride). This specification discusses a plasma procedure leading to a thin film of perfluoroalkyl groups upon a substrate, which will exhibit superhydrophobicity or oleophobicity. By this we mean that the surface will repel liquid with surface energies as low as that of acetone and alcohol.

15

The controlled deposition of many plasma polymers has been examined and the ratio of  $\text{CF}_2$  to  $\text{CF}_3$  is documented in terms of monomer type, plasma power levels and proximity to the glow region. We are now describing a new method for creating surfaces with greater coverage of functional groups which offers a novel approach to the creation of polymer surfaces by pulsed gas introduction to the plasma.

20

According to the present invention, a method of applying a fluoropolymer film to a porous or microporous or other body, comprises exposing the body to cold plasma polymerisation using a pulsed gas regime to form either (i) an adherent layer of unsaturated carboxylic (e.g. acrylic) acid polymer on the surface and then derivatising the polymer to attach a perfluoroalkyl group terminating in  $-\text{CF}_3$  trifluoromethyl, or (ii) a polymer of a perfluorocarbon monomer. A combination of electrical and gas pulsing may be used.

25  
30

Preferably, the cold method of applying a fluoropolymer film according to 1 and 2 wherein the cold plasma polymerisation uses a perfluorocarbon monomer or an unsaturated carboxylic acid.

5

The "gas on" and "gas off" times are preferably from 0.1 microsecond to 10 seconds.

The pulsed gas may be oxygen (except when perfluorocarbon monomer is used), or may be a noble or inert gas or H<sub>2</sub>, N<sub>2</sub> or CO<sub>2</sub>. Alternatively, acrylic acid polymer precursor or perfluorocarbon monomer may be pulsed directly without a process gas.

10

The body may be a film (not necessarily microporous) or of other geometry that allows coating by plasma polymerisation to a standard of consistency adequate for the end use.

15

The method may be stopped at any stage, when the applied film is continuous and impervious or at an earlier stage, when it is to a greater or lesser extent still apertured, i.e. has not yet completely filled in the underlying pores of the body. The pore size of the finished product can be set to any desired value by ceasing the method after an appropriate duration.

20

The plasma power is preferably 1W to 100W, more preferably 1.5W to 7W, except possibly where perfluorocarbon monomer is used.

The invention extends to the body with the thus-applied film. The substrate material of the body may be carbonaceous (e.g. a natural material such as cellulose, collagen or alginate, e.g. linen), synthetic, ceramic or metallic or a combination of these.

25

Electrical pulsing of the radio frequency supply to the plasma is known. This technique can ensure a more rapid deposition and greater coverage of the substrate surface by the plasma polymer. We have utilised the plasma polymerisation of acrylic

30

acid, which again is known but using a pulsed gas regime and clearly there are many other possible unsaturated carboxylic acids available as monomers. It is believed that such functionalities impart a degree of biocompatibility to substrates and allow of cell culture experiments to be undertaken successfully upon such a surface even with  
5 difficult and sensitive cell lines.

By virtue of a derivatisation stage, the acid group may be reacted with a range of materials, for example perfluoralkylamines, to yield a surface rich in perfluoroalkylamide groups. In this way the surface would predominate in  $\text{CF}_3$   
10 functions. Additionally the use of fluorinated surfactants will similarly generate a surface film of lower energy than ptfe and find application in for example the packaging market where oleophobic materials are desirable.

In the packaging market, there is a need for oleophobic venting films where the  
15 contents of a vessel or a package may require the release of a differential pressure. Such pressure differentials may arise from expansion or contraction of the container or the liquid contents, with changes in the ambient temperature or pressure. The liquid contents must be retained without leakage and so porous venting aids are used. In those situations where liquids of low surface tension are involved e.g. surfactants,  
20 detergents, or organic solvents, then conventional porous ptfe materials are not as efficient. The surface energy of such materials is of the order of 18 to 20 dynes/cm at  $20^\circ\text{C}$  and the energy of a  $\text{CF}_3$  surface is less at perhaps 6 dynes/cm, and can be influenced by the plasma conditions used for the deposition. It is also known that the substrate morphology can influence the value of the contact angle since surfaces of a  
25 certain roughness can lead to composite angles. The surface which has the greatest number of  $\text{CF}_3$  groups packed together will have the lowest surface energy.

Products having superior (high density) surface coverage, rapidly deposited, may arise from gas pulsing alone or in combination with R.F. pulsing. Such materials have  
30 application in filtration, chromatography, medical device and laboratory ware. For

example low cost thermoplastics could be coated using perfluorocarbon monomers to afford ptfe-like properties.

5 The body or substrate upon which the superhydrophobic layer is attached may be a carbonaceous polymer, e.g. a fluoropolymer such as ptfe, optionally itself a film, which may be porous or microporous. The process can also be applied to other polymers such as polyethylene and a range of other materials used for the biocompatible properties conferred by the acidic groups. Additionally by conversion to functionalities terminating in perfluoroalkyl groups the superhydrophobic  
10 properties of the closely spaced  $\text{CF}_3$  groups can be utilised. In certain applications it is commercially attractive to change the surface properties of low cost materials such that they become superhydrophobic. For example cellulose or polyurethane foam are used for their absorbent nature in wound dressings and incontinence and other sanitary products. By virtue of the hydrophobic layer being present the wicking effect  
15 can be directed and the flow of exudate or moisture constrained. Similarly for fluids with lower surface tension a superhydrophobic or oleophobic layer would offer the same mechanism.

A specific embodiment of the invention will now be described by way of example  
20 with reference to the accompanying drawings (all graphs), in which:

Fig 1 shows C(1s) XPS peak fit for 2 W continuous wave plasma polymer of acrylic acid.

25 Fig 2 shows continuous wave plasma polymerisation of acrylic acid as a function of power: (a) Q1s) XPS spectra; and (b) O/C ratio and percentage retention of acid functionality.

Fig 3 shows C(1s) XPS spectra for electrically pulsed plasma polymerisation of acrylic acid: (a) as a function of  $T_{\text{on}}$  ( $T_{\text{off}} = 4 \text{ ms}$  and  $P_p = 5 \text{ W}$ ); and (b) as a function of  $T_{\text{off}}$  ( $T_{\text{on}} = 175 \mu\text{s}$  and  $P_p = 5 \text{ W}$ ).

30 Fig 4 shows dependence on average power of: (a) oxygen : carbon ratios; and (b) percentage acid group incorporation for continuous wave; and electrically pulsed

plasma polymerisation of acrylic acid as a function of  $T_{on}$  ( $T_{off} = 4$  ms and  $P_p = 5$  W and 70 W) and  $T_{off}$  ( $T_{on} = 175$   $\mu$ s and  $P_p = 5$  W).

Fig 5 shows variation in the O/C ratio and percentage acid group incorporation during electrical and gas pulsed plasma polymerisation of acrylic acid using different gases ( $T_{on} = 175$   $\mu$ s  $T_{off} = 4$  ms and  $P_p = 5$  W).

Fig 6 shows electrical and gas pulsed plasma polymerisation of acrylic acid using oxygen as a function of  $T_{on}$  ( $T_{off} = 4$  ms and  $P_p = 5$  W): (a) C(1s) XPS spectra; and (b) O/C ratio and percentage acid group retention.

Fig 7 shows 2 W continuous wave plasma polymerisation of acrylic acid as a function of oxygen pressure: (a) C(1s) XPS spectra; and (b) O/C ratio and percentage retention of acid functionality.

Fig 8 shows electrical and gas pulsed plasma polymerisation of acrylic acid with oxygen as a function of  $T_{off}$  ( $T_{on} = 175$   $\mu$ s and  $P_p = 5$  W): (a) C(1s) XPS spectra; and (b) O/C ratio and percentage acid group retention.

Fig 9 shows ATR-IR spectra of: (a) acrylic acid monomer; and (b) Electrical and gas pulsed plasma polymer of acrylic acid, using oxygen, deposited on polyethylene ( $T_{on} = 175$   $\mu$ s,  $T_{off} = 4$  ms, and  $P_p = 5$  W), and

Fig 10 shows XPS spectra of plasma polymerisation of acrylic acid under CW, electrically pulsed and electrically-and-gas pulsed plasma conditions

All plasma polymerisations were performed in an electrodeless cylindrical glass reactor (50 mm diameter) enclosed in a Faraday cage. The reactor was pumped by a two stage rotary pump (Edwards E2M2) via a liquid nitrogen cold trap (base pressure of  $5 \times 10^{-3}$  mbar). Power was supplied from a 13.56 MHz source to a copper coil (10 turns) wound around the plasma chamber via an L-C matching unit and power meter.

Prior to each experiment, the reactor was scrubbed clean with detergent, rinsed with isopropyl alcohol, oven dried and further cleaned with a 50 W air plasma ignited at a pressure of 0.2 mbar for 30 minutes. A glass slide which had been washed in detergent, then ultrasonically cleaned in 1: 1 cyclohexane and IPA for one hour, was

positioned at the centre of the copper coils and the system pumped back down to base pressure.

Before polymerisation the acrylic acid (Aldrich 99%) was subject to several freeze  
5 thaw cycles and used without further purification. The monomer vapour was admitted  
via a needle valve (Edwards LV 10K) to a pressure of 0.2 mbar for 2 minutes prior to  
ignition of the plasma. If gas was also to be added it was introduced via a needle valve  
(Edwards LV 10K) to the required pressure. For gas pulsing experiments, gas was  
10 pulsed into the system by a gas pulsing valve (General Valve Corporation  
91-110-900) driven by a pulse driver (General Valve Corporation Iota One). Both  
continuous wave and pulsed plasma polymerisations were performed for 10 minutes.

For pulsed plasma experiments the R.F. generator was modulated by pulses with a 5  
V amplitude supplied by the pulse driver used to drive the gas pulsing valve. Pulse  
15 outputs from both the pulse generator and the R.F. generator were monitored by an  
oscilloscope (Hitachi V-252). For experiments involving both gas and electrical  
pulsing the pulse driver was used to simultaneously supply the gas pulsing valve and  
the R.F. generator. Thus the gas pulsing valve was open while the plasma was on.

20 Upon termination of the plasma, the reactor system was flushed with monomer and  
gas (where applicable) for a further 2 minutes, and then vented to air. Samples were  
then immediately removed from the reactor and affixed to probe tips using double  
sided adhesive tape for analysis.

25 A Vacuum Generators ESCA Lab Mk 5 fitted with an unmonochromated X-ray  
source ( $\text{Mg K}\alpha = 1253.6 \text{ eV}$ ) was used for chemical characterisation of the deposited  
films. Ionised core electrons were collected by a concentric hemispherical analyser  
(CHA) operating in constant analyser energy mode ( $\text{CAE} = 20 \text{ eV}$ ). Instrumentally  
determined sensitivity factors for unit stoichiometry were taken as  $\text{C(1s)} : \text{O(1s)} :$   
30  $\text{N(0s)} : \text{Si(2P)} = 1.00 : 0.39 : 0.65 : 1.00$ . The absence of any  $\text{Si(2p)}$  XPS feature  
following plasma polymerisation was indicative of complete coverage of the glass



substrate. A Marquardt minimisation computer program was used to fit peaks with a Gaussian shape and equal full width at half-maximum (FWHM).

## Results

5 Figure 1 shows the C(1s) envelope obtained by XPS analysis of acrylic acid plasma polymer. Five different carbon functionalities were fitted:  $\text{C}_x\text{H}_y$  (285 eV),  $\text{C}-\text{CO}_2$  (285.7 eV),  $\text{C}-\text{O}$  (286.6 eV),  $\text{O}-\text{C}-\text{O}/\text{C}=\text{O}$  (287.9 eV), and  $\text{C}-\text{O}_2$  (289.0 eV). The hydrocarbon peak was used as a reference offset. The oxygen : carbon ratio was calculated by dividing the oxygen peak area (after the sensitivity factor had been  
10 taken into account) by the carbon peak area. The relative amounts of acidic carbon atom retention was compared by calculating the percentage of  $\text{C}-\text{O}_2$  functionality relative to the total C(1s) area.

Continuous wave experiments were carried out at discharge power between 1.5 and 7  
15 W, Figure 2. As reported in earlier studies greater oxygen incorporation and acid group retention is achieved on decreasing the power of the discharge. The best results were found at a discharge power of 1.5 W which gave an O/C ratio of  $0.52 \pm 0.02$  and an acid group retention of  $18\% \pm 1$ .

20 This is considerably less than the oxygen : carbon ration of 0.67 and an acid group of 33% anticipated from the monomer structure. Various electrical pulse plasma polymerisation experiments were investigated in an attempt to improve retention of the monomer structure, Figures 3 and 4. It was found that decreasing the average power of a pulse modulated plasma discharge, by systematically reducing the plasma  
25 ontime or increasing the time-off, enhances oxygen incorporation and acid group retention in the plasma polymer. Both the oxygen : carbon ratio and the level of acid group retention found under the lowest average power conditions are significantly greater than found for the continuous wave experiments. The O/C ratio at the lowest average power was found to be  $0.72 \pm 0.03$  and the acid group retention was  $30\% \pm 1$ .

30

Pulsed addition of various gases was found to increase O/C ratios, Figure 5. The percentage acid group showed less variation except when the gas used was oxygen. A large increase, well above monomer values, in both the O/C ratio and acid group retention is evident when oxygen is added to the plasma.

5

Gas and electric pulse time-on greatly influence the plasma polymer composition, Figure 6; at gas and electrical pulse on times below approx. 130  $\mu$ s, the electrical power of the plasma is dominant. The effect of oxygen in the system is negligible. Decreasing the time-on increases the functionality of the plasma polymer. Beyond  
10 140  $\mu$ s the oxygen partial pressure in the system becomes non trivial. The composition of the thin films produced are altered markedly by this increase in the partial pressure of oxygen reaching a maximum at approx. 175  $\mu$ s. Under these conditions the oxygen : carbon ratio was  $1.00 \pm 0.04$  and the percentage acid group was  $43\% \pm 2$ .

15

Continuous wave polymerisation in the presence of oxygen has a direct influence on the functionalisation of films formed, Figure 7. Increasing the oxygen content in a low power continuous wave plasma increases the O/C ratio and the percentage acid group retention. the effect is less pronounced than for pulsed modulated systems.

20

Increasing the plasma and gas time-off for the electrical and gas pulsed plasma polymerisation of acrylic acid using oxygen decreases the functionalisation of the films produced, Figure 8. This is the opposite to the trend reported above for the electrically pulsed polymerisation of acrylic acid alone and it may be attributed to the  
25 decrease in oxygen content of the plasma with increasing gas time-off.


The ATRAR spectrum of the acrylic acid monomer has the following peaks, Figure 9a: O-H stretch ( $3300-2500\text{ cm}^{-1}$ ), C-H stretch ( $2986-2881\text{ cm}^{-1}$ ), C=O stretch ( $1694\text{ cm}^{-1}$ ), C=C stretch ( $1634\text{ cm}^{-1}$ ), O-H bend ( $1431\text{ cm}^{-1}$ ), C-O stretch ( $1295-1236\text{ cm}^{-1}$ ),  
30 C-H out-of-plane bend ( $974\text{ cm}^{-1}$ ), O-H out-of-plane bend ( $918\text{ cm}^{-1}$ ), and  $=\text{CH}_2$  wagging ( $816\text{ cm}^{-1}$ ). An ATR-IR of the plasma polymer deposited onto polyethylene,

Figure 9b, demonstrates a large amount of oxygen functionalisation with the O-H bend and C=O stretches clearly evident.

To optimise the derivatisation of the poly(acrylic acid) or similar layer with  
 5 fluorinated surfactant, the reaction between a carboxylic acid (or e.g. ethylene oxide or styrene oxide) and a fluorinated amine may be used. The fluorinated surfactant may be for example

Dupont FSD™, a commercially available fluorinated surfactant with a terminal CF<sub>3</sub>  
 10 group, the opposite end possessing a cationic head based on a substituted ammonium ion, or


Hoechst AG 3658™



15 Fluoroalkyl trialkyl ammonium salt.

Formation of the sodium salt of the poly(acrylic acid) PAA is followed by reaction with a solution of the fluorinated surfactant, the carboxylate anion and the cationic  
 20 fluorosurfactant forming a salt with the fluoro-chain (terminating in a CF<sub>3</sub> group) uppermost.

e.g.



An alternative route involves a further cold plasma step using sulphur hexafluoride,  
 30 SF<sub>6</sub>. This reagent will yield CF<sub>3</sub> groups when reacted with carboxylic acids or with esters.

Double pulsing could be carried out on other plasma polymer systems – for example with fluorinated monomers like perfluorohexane or even perfluorocyclohexane, to encourage the preferential coating by  $\text{CF}_3$  rather than  $\text{CF}_2$ . The pulsing technique  
5 allows one polymerisation pathway to be favoured over another by changing the time on and time off periods for the plasma, so influencing the reaction kinetics.

A very high degree of functional group control has been achieved by the combined pulsing techniques; see figure 10.

10

Claims

1. A method of applying a fluoropolymer film to a porous or microporous or other body, comprising exposing the body to cold plasma polymerisation using a pulsed gas regime to form either (i) an adherent layer of unsaturated carboxylic (e.g. acrylic) acid polymer on the surface and then derivatising the polymer to attach a perfluoroalkyl group terminating in  $-\text{CF}_3$  trifluoromethyl, or (ii) a polymer of a perfluorocarbon monomer.
2. A method of applying a fluoropolymer film according to claim 1 wherein a combination of electrical and gas pulsing is used.
3. A method of applying a fluoropolymer film according to claim 1 or 2 wherein the cold plasma polymerisation uses a perfluorocarbon monomer or an unsaturated carboxylic acid.
4. A method of applying a fluoropolymer film according to claim 1, 2 or 3 where both the "gas on" and "gas off" times are from 0.1 microsecond to 10 seconds.
5. A method according to any preceding claim, wherein perfluorocarbon monomer is not used and wherein the pulsed gas used is oxygen.
6. A method according to claim 1, 2, 3, or 4 wherein the pulsed gas used is a noble or inert gas or is hydrogen, nitrogen or carbon dioxide.
7. A method according to claim 2, 3, or 4 wherein acrylic acid polymer precursor or perfluorocarbon monomer is pulsed directly without a process gas.
8. A method according to any preceding claim wherein the body is not microporous.

9. A method according to any preceding claim, wherein perfluorocarbon monomer is not used and wherein the plasma power applied is in the range 1 Watt to 100 Watt.
- 5 10. A method according to claim 9, wherein the plasma power applied is 1.5 Watt to 7 Watt.
11. A body having a hydrophobic surface obtained by a method according to any preceding claim.
- 10 12. A body according to claim 11, whose substrate is carbonaceous, ceramic, metallic or a combination of these.

1/17




Fig.1

2/17




Fig. 2a



3/17




Fig. 2b

4/17




Fig. 3a

5/17




Fig. 3b

6/17




Fig.4a

7/17




Fig.4b

8/17




Fig. 5

9/17




Fig.6a

10/17




Fig. 6b



11/17




Fig.7a

12/17




Fig. 7b

13/17




Fig. 8a

14/17




Fig. 8b

15/17




Fig. 9a

16/17




Fig. 9b

17/17




Fig. 10

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 98/03838

**A. CLASSIFICATION OF SUBJECT MATTER**  
IPC 6 B05D7/24

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B05D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 97 42356 A (MASSACHUSETTS INST TECHNOLOGY) 13 November 1997 see the whole document ---	1,8,11
A	DATABASE WPI Section Ch, Week 8242 Derwent Publications Ltd., London, GB; Class A14, AN 82-89224E XP002099860 & JP 57 147514 A (MITSUBISHI CHEM IND LTD) , 11 September 1982 see abstract ---	1
A	FR 2 465 761 A (GORELIK RUDOLF) 27 March 1981 see the whole document -----	1

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

15 April 1999

Date of mailing of the international search report

23/04/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Brothier, J-A



# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 98/03838

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9742356 A	13-11-1997	NONE	
FR 2465761 A	27-03-1981	SU 1085995 A	15-04-1984
		CH 645656 A	15-10-1984
		DE 3036027 A	09-04-1981
		GB 2062655 A,B	28-05-1981
		US 4374180 A	15-02-1983